

RUBBER SOLUTION LUCON GP ST

DESCRIPTION

Rubber solution LuCon GP ST is meant for hot splice vulcanization and hot repairs of general purpose steel cord conveyer belts, based on SBR elastomers.

APPLICATION

- Surface preparation :
Surface must be clean, dry, free of oil and grease.
Splice must be prepared according to Lutze splicing instructions.
- Applying the solution :
Stir the solution thoroughly before opening the can. Apply the solution evenly and allow the coat to dry completely for 45 – 60 min. Then join the surfaces together and press the entire area.
- Vulcanization :
The conditions of vulcanization (temperature , time, pressure) can be found on the Lutze splicing instructions.

PROPERTIES

Consumption of solution	Ca. 1 liter/m ²
Minimum shelf life	6 months
Storage conditions	Dry cool (max 25°C) frost-free dark can tightly closed
Color	Black

AVAILABLE CONTAINER SIZES

Amount	container	Art. No .
1 l	can	CA3360